

# EMACO<sup>®</sup> S88C (Thixotropic) with MCI

Cementitious trowel applied shrinkage compensated structural repair mortar with MCI (Migrating Corrosion Inhibitor)

## DESCRIPTION

**EMACO S88C with MCI** is a ready-to-use, high strength repair mortar containing MCI. Mixed with water, it provides a rheoplastic, non-segregating, thixotropic mortar with high bond to steel and concrete.

**EMACO S88C with MCI** is synthetic fibre reinforced. It does not contain metallic aggregate and is free of chlorides.

## RECOMMENDED FOR

**EMACO S88C with MCI** is recommended for repairs needing mortar layers up to 40mm in thickness.

- Maintenance works at ports or sea-areas.
- Maintenance works at mechanical industries, especially in conditions where mineral oils, lubricants, etc. are present.
- Protection of concrete against aggressive waters containing sulphates, sulphides, chlorides, etc.
- Repair of damaged concrete members.
- Repair of concrete members subjected to repetitive stresses.
- Repair of structural members (reinforced or pre-stressed beams under normal or eccentric stress).
- Vertical, overhead and horizontal applications.

## FEATURES AND BENEFITS

- Economical
- Durable
- Highly impermeable
- Ready-to-use
- Shrinkage compensated
- Sprayable
- Sulphate resistant
- Excellent workability
- No added chloride
- Contains non-corroding synthetic fibres
- High early and final strengths
- Favourable E-Modulus
- With added MCI

**EMACO S88C with MCI** is a ready-to-use powder that merely has to be mixed with water to yield an easily workable, shrinkage compensating repair mortar.

**EMACO S88C with MCI** is resistant to aggressive environmental elements such as seawater, carbon dioxide, air pollution etc.

**EMACO S88C with MCI** mortar is shrinkage compensated both in the plastic and in the hardened state. It is impermeable and extremely durable even in aggressive conditions.

By virtue of its uniformly dispersed synthetic fibres, **EMACO S88C with MCI** can be either sprayed or trowelled onto horizontal, vertical and also overhead sections.

## TYPICAL PERFORMANCE DATA

	1 Day	28 Days
Compressive Strength	30 MPa	70 MPa
Flexural strength	4.5 MPa	8 MPa
E-Modulus		30 GPa
Bond to concrete		>3.0 MPa
to steel (smooth)		4 MPa
(deformed)		30 MPa

## PROPERTIES

Supply form	powder
Water added per bag (20kg)	3.0 - 3.4 litres
Colour	grey
Specific Gravity (mixed)	approx. 2.2
Storage temperature	moderate
Application temperature	not below 5°C
Effect of humidity	same as cement
Physiological effects	same as cement
Toxicity	non-toxic

## APPLICATION

### Substrate Condition

Surfaces to which **EMACO S88C with MCI** mortar are applied, should be clean, sound and free of dust or loose particles. Cement laitance, oil, grease, mould release oil or curing compound must be removed from concrete surfaces by using high pressure water jetting (1100-2500 Bar), or bush hammer, scabblers, gritblasting or other approved means. Cut edges of recess or crack vertically, to a depth of at least 10mm. This step is very important, as **EMACO S88C with MCI** needs a rough surface to achieve maximum grip. All absorbent substrate surfaces must be thoroughly wetted down to saturate all pores. During application, the temperature of the substrate should not be below 5°C. If the mortar must be thicker than 25mm, anchor welded wire reinforcement to the concrete to be treated leaving space between the mesh and the surface. The successive cover of **EMACO S88C with MCI** over reinforcement must be at least 10mm thick. If application thickness is less than 25mm, no mesh is needed, provided that the surface has been roughened with ridges of approximately 5mm in height, in order to provide the needed restraint to the mortar expansion.

### Mixing

Pour minimum required water into a suitable mixer and add **EMACO S88C with MCI** rapidly and continuously while mixing. Mix for 3-4 minutes or until a lump free, homogeneous mortar is obtained.

Add extra water, if necessary, until the required consistency is obtained and mix again for 2 - 3 minutes.

The amount of water to be added is highly dependent on ambient temperature and relative humidity. In hot and dry climates, slightly higher amounts of water may be necessary, the contrary in cold and humid climates.

# EMACO<sup>®</sup> S88C (Thixotropic) with MCI

Water requirement to produce EMACO S88C with MCI thixotropic mortars:

Mixing	Type of Applic.	Rec. Consist.	Flow ASTM C-230*	Mixing Water	
				Min.	Max.
By Mixer	Spray Trowel	Plastic Plastic	70% 45%	15% 15%	16% 16%

\* Test method was modified to 5 drops

## Priming

No special primer is required. To obtain extra strong bonding, the damp substrate can be primed with a slurry brush coat of **EMACO S88C with MCI** (2 parts of powder to 1 part of water).

## Method of use

**EMACO S88C with MCI** can either be sprayed or trowelled. If necessary, a wooden float may be used to level the surface. The final surface may be smoothed as desired by a wooden, plastic or synthetic sponge trowel. Trowelling after the spray application may start only when the mortar has set, that is, when fingers do not sink beneath the surface, but mark it lightly.

## Tools

Mixing: low speed drill with suitable helical paddle (jiffy) or by pan mixer. Hand mixing of **EMACO S88C with MCI** is not recommended to avoid the introduction of excessive amounts of water.

Applic.: by trowel, float or spatula, wet sprayer (worm gear type).

Finish: wood or steel trowel; plastic sponge trowel for very smooth texture.

## CURING

In normal ambient conditions, even without traditional curing, **EMACO S88C with MCI** will not craze or crack due to plastic shrinkage, as often occurs with mortars, which are not protected adequately in the first 24 hours of curing. Cover with plastic sheet for 24hrs or apply **MASTERKURE 402** liberally to surface to achieve optimum results. Do not immerse in water to cure.

## CLEANING

Tools should be cleaned with water before the material hardens.

## ESTIMATING DATA

A 20kg bag of **EMACO S88C with MCI** mixed with 3.2 litres of water yields 10.5 litres (0.0105m<sup>3</sup>), therefore material requirement is 19.1kg/m<sup>2</sup> at 10mm thickness.

## POT LIFE

Temp °C	Setting times of EMACO S88C with MCI	
	Initial (hrs)	Final (hrs)
5	2.00	3.00
20	1.45	2.45
40	1.00	2.00

At consistency of 45% flow at flow table (ASTM C-230) 5 drops

## PACKAGING

**EMACO S88C with MCI** is available in 20kg moisture resistant bags.

## SHELF LIFE

**EMACO S88C with MCI** can be stored in tightly sealed original bags for 12 months, if kept dry and at moderate temperature.

## PRECAUTIONS

Do not use **EMACO S88C with MCI** thixotropic mortar:

- For precision grouting, use **MASTERFLOW 880** Grout or **MASTERFLOW 870** Grout.
- In contact with water with pH less than 5.5.

**EMACO S88C with MCI** contains non-toxic, non-mineral fibres, which are not a known health hazard. As with other products containing Portland cement it has an alkaline nature and thus can be irritating to skin and eyes. Wear simple dust masks, goggles and gloves when handling. Wash off splashes of mortar with clean water. If irritation persists seek medical advice. For full safety and first aid instructions, refer to the product Material Safety Data sheet. Keep out of reach of children.

AES88CMCI/6/1011

## STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this **BASF** publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

## NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by **BASF** either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not **BASF**, are responsible for carrying out procedures appropriate to a specific application.

**BASF Australia Ltd**  
A.B.N. 62008437867  
Head Office: 11 Stanton Road Seven Hills, NSW 2147  
Ph. (02) 8811 4200

Newcastle (02) 4961 3819  
Canberra (02) 6280 6010  
Brisbane (07) 3633 9900  
Townsville (07) 4774 7344  
Melbourne (03) 9549 0300

Adelaide (08) 8139 7500  
Perth (08) 9366 2600  
Darwin (08) 8984 3269  
Kalgoorlie 0417 772 355

**BASF New Zealand Ltd**  
**BASF WEB SITES**

Head Office: 45 William Pickering Drive, Albany, Auckland Ph: (09) 414 7233  
www.basf-cc.com.au www.basf-cc.co.nz www.meyco.basf.com