

MasterSeal[®] M 881 (formerly known as Conipur WC 881)

A wear coat for use in car park deck waterproofing systems

DESCRIPTION

MasterSeal M 881 is a wear coat for use in car park deck waterproofing systems. It is a solvent free, 2- component polyurethane and is slightly thixotropic so that it can be applied to ramps without the on-site addition of a thixotrope as well as to horizontal surfaces. It has a low consumption for economic use and exhibits an excellent bond to the waterproofing membrane. **MasterSeal M 881** is slightly elastic so that it can accommodate some movement of the deck. It has a tenacious hold onto the broadcast aggregate providing a hard wearing, skid resistant surface

RECOMMENDED USES

MasterSeal M 881 is primarily intended for use as the wear coat in MasterSeal Traffic car park deck waterproofing systems. It can also be used in other systems where its low consumption and ease of application together with its excellent mechanical properties can be used to advantage.

FEATURES AND BENEFITS

- **Long lasting non slip profile** - Tenacious hold to broadcast aggregate
- **Multi-purpose** - Slightly thixotropic for application to ramps
- **Withstands loads imposed by traffic** - Excellent bond to waterproofing membrane
- **Suitable for prolonged use in carparks** - Resistant to fuels, battery acid and hydraulic oils

PROPERTIES

Mixing ratio	by weight		100 : 46
Mixed density	at 23° C	g/mm ²	1.08
Mixed viscosity	at 23° C / 50 s ⁻¹	mPas	1400
Working time	at 23° C	min	30
Substrate and ambient temperatures		° C ° C	min. 5 max. 40
Relative humidity		%	max. 80

Technical Data cured material

Shore D hardness			65
Tensile strength	DIN 53504	N/mm ²	16.0
Elongation	DIN 53504	%	50

The above figures are intended as a guide and should not be used as the basis for specifications.

APPLICATION

MasterSeal M 881 is supplied in working packs which are pre-packaged in the exact ratio. Before mixing, precondition both A and B components to a temperature of approximately 15 to 25 °C. Pour the entire contents of part B into the container of part A. **DO NOT MIX BY HAND.** Mix with a mechanical drill and paddle at a very low speed (ca. 300 rpm) for at least 3 minutes. Scrape the sides and the bottom of the container several times to ensure complete mixing. Keep the mixer blades submerged in the coating to avoid introducing air bubbles. **DO NOT WORK OUT OF THE ORIGINAL CONTAINER.**

After proper mixing to a homogeneous consistency pour the mixed parts A and B into a fresh container and mix for another minute. **MasterSeal M 881** should be spread with a squeegee and finished by rolling.

The curing time of the material is influenced by the ambient, material and substrate temperatures. At low temperatures, the chemical reactions are slowed down; this lengthens the pot life, open time and curing times. High temperatures speed up the chemical reactions thus the time frames mentioned above are shortened accordingly.

To fully cure, the material, substrate and application temperature should not fall below the minimum. Following application the material should be protected from direct contact with water for approx. 16 hours. The temperature of the substrate must be at least 3°C above the dew point both during the application and for at least 16 hours after application (at 15 °C).



The Chemical Company

MasterSeal[®] M 881 (formerly known as Conipur WC 881)

The coating to which **MasterSeal M 881** is to be applied should be clean and dry. Application should take place within the re-coating intervals of the surface to which it is to be applied.

ESTIMATING DATA

The consumption of **MasterSeal M 881** is 0.4 – 0.7 kg/m². In some countries the minimum thickness of the wear coat is defined. In these cases the consumption can be higher than the values quoted above.

The above consumption figures are intended as a guide only and may be higher on very rough or porous substrates.

PACKAGING

MasterSeal M 881 is supplied in 24 kg working packs.

SHELF LIFE

MasterSeal M 881 has a shelf life of 12 months. Store out of direct sunlight, clear of the ground on pallets protected from rainfall.

PRECAUTIONS

For the full health and safety hazard information and how to safely handle and use this product, please make sure that you obtain a copy of the BASF Material Safety Data Sheet (MSDS) from our office or our website.

® = registered trademark of BASF group in many countries

MasterSeal_M 881 ANZ v1 - 0414

RESPONSIBILITY The technical information and application advice given in this BASF publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE Field service where provided does not constitute supervisory responsibility. Suggestions made by BASF Construction Chemicals either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not BASF Construction Chemicals, are responsible for carrying out procedures appropriate to a specific application.

BASF Australia Ltd
ABN 62008437867
Construction Chemicals Division
11 Stanton Road Seven Hills, NSW 2147

Sales Offices:
Sydney, Brisbane, Melbourne, Adelaide,
Perth
Freecall: 1300 227 300

BASF Emergency Advice:
1800 803 440 within Australia (24hr)
0800 944 955 within New Zealand

BASF New Zealand Ltd
BASF WEB SITES

45 William Pickering Drive, Albany, Auckland, Phone: 0800 334 877
www.basf-cc.com.au www.basf-cc.co.nz