



The Chemical Company

SONOLASTIC® ULTRA

High performance polyurethane joint sealant

DESCRIPTION

Sonolastic Ultra is a one component, moisture curing, aliphatic polyurethane sealant. Aliphatic technology ensures **Sonolastic Ultra** will be UV resistant, non-chalking, non-staining, self cleaning and non pick, resulting in unmatched durability.

COMPLIANCES

- Federal Specification TT-S-00230C, Type II, Class A when primed.
- ASTM C 920, Type S, Grade NS, Class 25. Use NT, M, A, G and I.
- Corps of engineers CRD C-541, Type II, Class A.
- USDA approved for use in meat and poultry areas.
- Canadian approval for use in areas that handle food.

RECOMMENDED FOR

Active, exterior and interior joints that demand extreme UV resistance and long term colour integrity. **Sonolastic Ultra** can be used on both vertical and horizontal applications including trafficable surfaces on floors, panels, walls, window frames, curtain walls and precast panels. Substrates include concrete, masonry, brick, aluminium and timber.

Pick resistance finds applications in shop fronts, prisons, schools, public amenities and buildings.

FEATURES AND BENEFITS

- **Aliphatic polyurethane technology**
Non-staining, non-yellowing, non-chalking.
- **High UV resistance**
No discolouration from sunlight
- **Medium modulus**
Excellent puncture and abrasion resistance
- **Improved gunability and workability**
Easy tooling
- **Pick resistant**
Security applications
- **Suitable for non-chlorinated water immersion situations**
No swelling or softening
- **Movement capability $\pm 25\%$**
Expands and contracts with joint movement
- **Excellent Chemical Resistance**
Ideal in food or petroleum environments
- **No surface tackiness**
No dirt pickup, self-cleaning

PERFORMANCE DATA*

Property	Test Method	Value (Average)
Movement capability (MAF)	ASTM C 719	$\pm 25\%$
Tensile strength	ASTM D 412	4.1
Ultimate elongation at break	ASTM D 412	600%
Hardness at standard conditions (Shore A)	ASTM C 661	50 \pm 5
Tack-free time	ASTM C 679	Less than 72 hours
Stain and colour change	ASTM C 510	None
Volatile Organic Compounds (VOC)	SCAQMD Method 304-91	90g/litre
Service temperature range (°C)		-40 to 82

* The data represents information typically required to verify performance. For the full and comprehensive list of performance data, refer to "Application Guide & Performance Data for Sonolastic Polyurethane Sealants" available from your local BASF Construction Chemicals representative.

APPLICATION DIRECTIONS

For information on **joint design, surface preparation and priming**, refer to Technical Note 17 "Application Guide & Performance data for Sonolastic Polyurethane Sealants" available from your local BASF Construction Chemicals representative.

Application

- **Sonolastic Ultra** comes ready to use. Apply by professional caulking gun. Do not open cartridges or sausages, until preparatory work has been completed.
- Fill joints from deepest point to the surface by holding a suitably sized nozzle against the back of the joint.
- Dry tooling is recommended. DO NOT use soapy water when tooling. Tooling results in the correct bead shape, a neat joint, and maximum adhesion.

For Best Performance

- Do not allow uncured **Sonolastic Ultra** to come into contact with alcohol-based materials or solvents.
- Do not apply polyurethane sealants in the vicinity of uncured silicone sealants or uncured **Sonolastic 150** or **150 Tint Base**.
- **Sonolastic Ultra** should not come in contact with oil-based caulking, silicone sealants, polysulfides or fillers impregnated with oil, asphalt or tar.
- When **Sonolastic Ultra** is to be used in areas subject to water immersion, cure for 21 days at 25°C and 50% relative humidity. Allow longer cure time at lower temperatures and humidity.



The Chemical Company

SONOLASTIC® ULTRA

- Do not use in swimming pools or other submerged conditions where the sealant will be exposed to strong oxidizers. Avoid submerged conditions where water temperatures will exceed 50°C.
- Protect unopened containers from heat and direct sunshine.
- In cool or cold weather, store container at room temperature for at least 24 hours before using.
- Do not apply over freshly treated wood; treated wood must have weathered for at least 6 months.
- All horizontal applications require the use of a primer.
- Sonolastic Ultra** can be applied below freezing temperatures only if substrates are completely dry, free of ice or frost, and clean.
- Low temperatures will extend curing times.
- Substrates such as copper, stainless and galvanized typically require the use of a primer; **Primer 733** or **766** are acceptable. For Kynar coating use **Primer 733** only. An adhesion test is recommended for any other questionable substrate.
- Proper application is the responsibility of the user. Field visits by BASF Construction Chemicals Technical Representatives are for the purpose of making technical recommendations only and not for supervising or providing quality control on the jobsite.

COLOURS

A complete choice of standard colours is available including white, aluminium-grey.

CURING

The cure of **Sonolastic Ultra** varies with temperature and humidity. The following times assume 23°C, 50% relative humidity, and a joint 12mm width by 6mm depth.

- Skins - overnight or within 24 hours
- Functional within 3 days
- Full cure in approximately 1 week
- Immersion service: 21 days

Note: If joint thickness is more than 6mm, then cure period increases.

CLEANING

- Immediately after use, clean equipment with **Sonoshield Thinner**. Use proper precautions when handling solvents.
- Remove cured sealant by cutting with a sharp edge tool.
- Remove thin films by abrading.

ESTIMATING DATA

Joint Size (mm)	Metres per litre
5 x 5	40
10 x 10	10
12 x 12	6.95
15 x 7.5	8.88
20 x 10	5.00
25 x 12.5	3.20
30 x 15	2.22

PACKAGING

- 590ml Pro Pak sausages, 20 sausages to a carton

SHELF LIFE

Shelf life is 1 year for cartridges and sausages in their original, unopened packaging under normal conditions.

PRECAUTIONS

KEEP OUT OF REACH OF CHILDREN. Use only with adequate ventilation. Prevent contact with skin, eyes, and clothing. Wash thoroughly after handling. Use impervious gloves, eye protection and if the TLV is exceeded or used in a poorly ventilated area, use approved respiratory protection.

First Aid

In case of eye contact, flush thoroughly with water for at least 15 minutes. SEEK IMMEDIATE MEDICAL ATTENTION. In case of skin contact, wash affected areas with soap and water. If irritation persists, seek medical attention. Remove and wash contaminated clothing. If inhalation effects occur, remove to fresh air. If discomfort persists or any breathing difficulty occurs, or if swallowed, SEEK IMMEDIATE MEDICAL ATTENTION. Refer to Material Safety Data Sheet (MSDS) for further information.

All BASF Construction Chemicals Australia & New Zealand data sheets are updated on a regular basis, it is the user's responsibility to obtain the most recent issue ASonUltra/10/0408

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this **BASF Construction Chemicals** publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by **BASF Construction Chemicals** either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not **BASF Construction Chemicals**, are responsible for carrying out procedures appropriate to a specific application.

BASF Construction Chemicals Australia Pty Ltd
Incorporated in NSW A.B.N. 46 000 450 288
Head Office: 11 Stanton Road Seven Hills, NSW 2147
Ph. (02) 8811 4200

Newcastle	(02) 4961 3819	Adelaide	(08) 8139 7500
Canberra	(02) 6280 6010	Perth	(08) 9366 2600
Brisbane	(07) 3633 9900	Darwin	(08) 8984 3269
Townsville	(07) 4774 7344	Kalgoorlie	0417 772 355
Melbourne	(03) 9549 0300		

BASF Construction Chemicals New Zealand Ltd Head Office: 45 William Pickering Drive, Albany, Auckland Ph: (09) 414 7233
BASF WEB SITES www.basf-cc.com.au www.basf-cc.co.nz www.basf-ugc.com