



ELASTO-THANE 230 SL

SELF-LEVELING JOINT SEALANT

1. PRODUCT NAME

ELASTO-THANE 230 SL

ELASTO-THANE 230 SL is a one-part, self-leveling, non-staining, polyurethane sealant which cures at ambient temperature to a firm, flexible tear-resistant rubber. It is highly resilient and has excellent recovery characteristics after extended periods of compression or elongation.

2. MANUFACTURER

PACIFIC POLYMERS INTERNATIONAL, INC.
12271 Monarch Street
Garden Grove, CA 92841
714/898-0025
FAX (714) 898-5687

3. PRODUCT DESCRIPTION

Composition: Polyurethane based joint sealant.

Basic Uses: For sealing and caulking joints that are subject to contraction and expansion. Bonds to concrete, wood, glass, and metal.

Limitations: Containers that have been opened must be used up within one or two days since it is a moisture-reactive material. It sets up when exposed to air. All surfaces must be completely free of foreign matter. When a faster, or more predictable, cure time is required, our Elasto-Thane 227 or Elasto-Thane 920 should be used.

Colors: Concrete Grey

Standard Packaging: 30oz. cartridges, 5 gallon pails are available upon request.

Standards:

ASTM C-920, Type S, Class 12.5, Use T,
Federal Specification TT-00230C, Class A, Type I

WARNINGS AND HAZARDS:

Before using the products, always refer to MSDS for important warnings and safety information. Use only in areas with adequate ventilation. Avoid breathing vapors. Keep away from heat and flame. Avoid contact with eyes and skin. In the

event of skin contact, remove immediately and wash with warm, soapy water. Wear suitable eye protection. Always wash hands before eating.

4. TECHNICAL DATA

(See Page 3 for technical data.)

5. INSTALLATION

Joint Design: Suitable for all properly designed joints following accepted engineering practices.

Joint width must be a minimum of 4 times the anticipated movement.

Surface Preparation: All joints must be absolutely clean and dry. For concrete, sandblasting is recommended. All curing compounds, old caulks, grease, waterproofing compounds, etc., must be removed. For non-porous surfaces, such as glass, metal, etc, cleaning with M.E.K. or Toluene is recommended. Polyethylene rod or polyurethane foam is recommended as a joint-filler and back-up material. Sand, other caulks, incompressibles, fillers treated with bituminous products, grease or oil, should not be used. Where present, they must be removed or separated by vinyl tape or polyethylene film. Some surfaces may require the use of DECK-THANE PRIMER or METAL PRIMER.

Application: No mixing or measuring is required, as the **ELASTO-THANE 230 SL** is a single component, moisture cured material. Apply by caulking gun or hand-pressure-type equipment, or pour directly from the container.

6. AVAILABILITY AND COST

ELASTO-THANE 230 SL is supplied through building material dealers. Prices vary with quantity and packaging. Quotations are made on request.

These products are designed and manufactured to be installed by professional installers familiar

with surface preparation and application procedures. All others should consult a professional installer; those who choose to install these products without professional assistance do so at their own risk.

7. PRODUCT WARRANTY

Satisfactory results depend not only upon quality products but also upon factors beyond our control; methods of application and site conditions are examples of such factors and can affect product performance. This warranty consequently extends only to products installed in strict accordance with the manufacturer's specifications.

It is the users responsibility to satisfy himself, by his own information and tests, of the suitability of the product for his own intended use; user assumes all risk and liability resulting from his use of the product. The substrate to which the product is applied must be sound structurally and otherwise. Structural or substrate failures or imperfections resulting in damage to or failure of the product are not covered by this warranty. Since the use of the product is beyond the control of the manufacturer, the manufacturer assumes no liability for misapplication and misuse of the product.

This warranty does not cover consequential damages, nor does it cover the labor attendant to replacing product in the event of a product failure. The warranty only extends to replacement of the product itself.

All products proven to be defective in manufacture will be replaced at no charge. Since the use of these products is beyond our control we cannot assume any risk or liability for results obtained,

nor can we accept damages in excess of the purchase price of these products.

8. MAINTENANCE

If **ELASTO-THANE 230 SL** is damaged, and the joint has not been contaminated, it can be repaired by cutting out the affected areas and resealing it with **ELASTO-THANE 230 SL**.

9. TECHNICAL SERVICES

All of the latest updates to product data and specifications are available at the Pacific Polymers International, Inc. website at www.pacpoly.com. Since product data and specifications change, it is the users responsibility to make certain the most current versions of product data and specifications are being used.

Technical assistance can be obtained by contacting:

PACIFIC POLYMERS INTERNATIONAL, INC.
 12271 Monarch Street
 Garden Grove, CA 92841
 714/898-0025
 FAX (714) 898-5687

WIDTH OF JOINT

| | INCHES | 1/4" | 3/8" | 1/2" |
|------------------------------------------------------|---------------|-------|-------|------|
| DEPTH OF JOINT | 1/4" | 308 | 205 | 154 |
| | 3/8" | | 136 | 102 |
| | 1/2" | | | 77 |
| Linear Feet Per Gallon of Elasto-Thane 230 SL | | | | |

4. TECHNICAL DATA – ELASTO-THANE 230 SL

| PROPERTY | TEST METHOD | RESULTS |
|---------------------------------------------------------------------|----------------------|---------------------------------|
| Consistency Type I | ASTM C-920 | Self-leveling |
| Service Temperature Range | --- | -40°F (-40°C) to 180°F (82.2°C) |
| Tackfree Time at 77°F (25°C); 50% R.H. | Fed. Spec. TT-S-230c | 16-24 hrs. |
| Movement Capability | ASTM C-719 | ± 12.5% |
| Tensile Strength at 77°F (25°C) | ASTM D-412 | 250 psi ± 10% |
| Extrudability | ASTM C-603 | 2 seconds |
| Weight Loss, after heat aging | ASTM C-792 | 9% |
| Cracking and Chalking, after heat aging | ASTM C-792 | None |
| Stain and color change | ASTM C-510 | Passes (no visible stain) |
| Bond Durability (±12.5% movement) (on glass, aluminum, concrete) | ASTM C-719 | No Failure |
| Accelerated Weathering model after 3000 hours | Atlas 6500 xenon arc | No elastomeric property damage |
| Cure Time at 77°F (25°C); 50% R.H. (@ 1/4"- 1/2" thickness) | Observed | 4-7 days |
| % Elongation | ASTM D-412 | 400 ±10% |
| Shrinkage | --- | Negligible |
| Hardness (Shore A) | ASTM D-2240 | 30 ± 5 |
| V.O.C. | | 0 |
| Specific Gravity | | 1.354 |
| Weight per gallon | | 11.28 lbs. per gal. |
