

PRODUCT	FLOOR SCREEDS // BRIEF DESCRIPTION	THICKNESS	CURE TIME (APPROX ONLY)	STRENGTH MPA	MIXED VOLUME PER KIT
DURABOND-SUPERFINE	Trowel applied, 2 part latex/cement based, general purpose floor levelling compound, interior/exterior; Coverage rate: 5.5m ² @ 3mm (24kg FLC powder + 4 litres FLC liquid).	0.5 - 5mm*	12-24 hours dry 24 hours overlay	30 Mpa	16 lt
HARDFAST	Trowel applied, very quick setting, patching compound. Recommended for small areas only. Interior dry areas only. Coverage rate: 3.8m ² @ 3mm.(10 kg Hardfast powder + and water to suit).	0 – 3mm*	20 minutes dry 45 minutes overlay	N/A	n/a
SUPASET UNIFLOOR	Supaset is a rapid setting standard trowel product. Mixes with 3.8—4.8 lts of water depending on thickness (use less water for thicker screeds). Unifloor: Economy , water only mix.; 20kg bag plus 4.5lts water.	0 –50mm	1—2 hrs dry	24 mpa	14 lts
ULTRAFINISH	Ultrafinish: Very smooth finishing compound; 15 kg bag; water as required.	0 – 30mm	4 -24 hrs	24mpa	14 lts
		Skim	2-4 hrs	Skim	
MATRIX	Trowel applied, 2 part latex/cement based general purpose floor levelling compound. Coverage rate: 12.5m ² @ 2mm (25kg Matrix powder + 5 litres Matrix liquid)	0 - 3mm*	12-24 hours dry 24-48 hours overlay	28 mpa	17 lt
SCREED 20+ PLUS	Trowel applied, heavy duty /cement based floor repair compound designed to deep fill with high adhesion and strength. Coverage rate: 0.7m ² @ 20mm (20kg Screed powder + 1.8—2.0 lts water). Can also be used for deeper fills (>20mm) with care using lower water levels.	5 - 20mm	24-48 hours dry 2-7 days overlay	28 Mpa	12 lt
MASTERTOP					
P505	Ultra fine, water mixed smoother. Can be fine finished to a feathered edge. Suitable for levelling over old lino or embossed vinyl. Coverage rate: approx 30m ² /4.5 kg pail	0 - 1mm*	1 hour dry 2 hours overlay	N/A	18 lt
P510	Trowel or pump grade, cement based, self levelling, self smoothing floor finishing compound. Easy application. 20 kg bags P510 4.8—5.0 lts water	0—30mm	approx. 2 hours dry	27	12.2 lts
P546	Very rapid set; 45 minute set, trowel mortar and smoothing compound, (20kg bag + 4.5—4.7 litres water)	0.5 - 50mm	1-2 hour overlay	28 Mpa	15lt



SELECTION CHART - FLOOR LEVELLING, SMOOTHING & REPAIR

Aug 2016

NOTE: * = Maximum recommended thickness per application. Most are normally intended for interior use.

email: ncpsales@nuplex.co.nz

Ph: 0508-882288 Fax 0508-553344

Web data: www.nuplexconstruction.co.nz

In all cases read the full datasheets before selecting and /or commencing.