

MANUAL SECTION	ISSUE DATE	AUTHORISED	REPLACES	PAGE
<i>Flooring Sealer</i>	<i>June 2001</i>	<i>PM</i>	<i>New Issue</i>	<i>1 of 2</i>

LOCKFAST PRIMER P610

DESCRIPTION

PRIMER P610 is a water-borne polymer emulsion suitable for the priming of concrete floors prior to the application of floor levelling compounds.

APPLICATIONS:

1. bonding new concrete to old. Bonding promoter of floor levelling compounds to old substrates.
2. Sealing of porous floors prior to bonding self adhesive products.

TYPICAL PROPERTIES

- Type: Water-borne emulsion
- Base: Vinyl polymer
- Colour: White, dries clear
- Flash Point: None, water based
- Density: Approximately 1.0 Kg/Lt

DIRECTIONS FOR USE:

Floor Preparation:

Concrete:

- Ensure that the concrete has an effective damp-proof membrane. The surface must be clean and free from dust, dirt, grease and other contaminants. Curing or releasing agents must be removed from concrete. A slight dampness may be tolerated although surface water must be removed.
- Levelling of floors may be done with Floroc, Matrix or FLC compounds. Levelled floors generally do not require sealing. If sanded, then sealing may be advantageous.

Damp Floors:

- Duraseal will not stop rising moisture. If in doubt about potential wet or damp floors, seal with Aquaguard 101 before proceeding.

No warranty either expressed or implied or statutory is made by NUPLEX in this document except as expressly stated in any sale and purchase agreement entered into between NUPLEX and the buyer.

This document is a technical data information sheet. The description of the product or products and the properties of the product or products contained in this document is for the sole purpose of identifying the product or products and describing their property or properties and does not constitute a warranty that the product or its properties shall conform to that description; nor is the description of the product and/or its properties a warranty by NUPLEX that the goods are suitable for a particular purpose.

NUPLEX CONSTRUCTION PRODUCTS

PO Box 1 2841, Penrose, Auckland Telephone 0-9-579 2029 Fax 0-9-525 3709 www.nuplexbuilding.co.nz email: bpdsales@nuplex.co.nz

H A M I L T O N	P A L M E R S T O N N O R T H	W E L L I N G T O N	C H R I S T C H U R C H
Telephone 0-7-847 8658	Telephone 0-6-353 3685	Telephone 0-4-477 7040	Telephone 0-3-366 6802
Fax 0-7-847 3766	Fax 0-6-353 3632	Fax 0-4-477 7039	Fax 0-3-365 7845

APPLICATION:**1. Self Adhesive Products**

Shake the container well. Apply P610 as supplied; **do not** dilute. Apply one coat by brush, roller or broom, avoiding areas of overlap or build-up. Allow to dry before the application of floor levelling compound. The drying time is dependant on temperature, room humidity and porosity of the substrate, however allow approximately 30 - 60 minutes. Self adhesive products may be applied as soon as the P610 is fully dry

Coverage: 5m²/Litre

2. Concrete or Self Levelling Bonding

Shake the container well. Mix P610 one part to two parts of water and apply to the floor by roller.

NB: Allow to **fully dry** prior to the application of levelling compounds.

- A coverage of approximately 6 square metres per litre should be obtained.
- **Note:** Porous substrates may require two or more coats.
- P610 should be laid over within 24 hours of application.

CLEAN-UP:

Use water to clean up instruments and hands.