

Technical Data Sheet

Soprema Flameless Membrane



Formerly known as SOPRALENE STICK HR 40

SOPRAPLY STICK DUO

TECHNICAL DATA SHEET 200610SCANE

(supersedes 200316SCANE)



WATERPROOFING

APPLICATIONS

ROOFS

DESCRIPTION

SOPRAPLY STICK DUO is a base sheet membrane composed of SBS modified bitumen reinforced with a composite reinforcement. The surface is sanded and the self-adhesive underface is covered with a silicone release film.

SOPRAPLY STICK DUO is provided with DUO SELVEDGE technology which allows the immediate sealing of the membrane along side laps.

SURFACE PREPARATION

Surfaces must be clean, dry and free of loose particles. The membrane is installed over the substrate previously primed with one of the ELASTOCOL STICK primers.

INSTALLATION

SELF-ADHESIVE

SOPRAPLY STICK DUO is adhered to the substrate by peeling off the silicone release film.

Once the membrane is in place, apply pressure over the whole surface using a membrane roller to ensure a complete and uniform adhesion.

When completing the end lap, apply ELASTOCOL STICK primer over the last 150 mm (6 in) of the membrane before installing the next membrane.

Finish the application by welding the last 25 mm (1 in) of the side lap using an electric hot-air welder and a membrane roller. The use of SOPRAMATIC automatic hot-air welder will greatly increase the speed and quality of the seal.

Application temperatures: 0°C (32°F).

FOR COMPLETE INFORMATION ON PRODUCT INSTALLATION, PLEASE CONSULT YOUR SOPREMA REPRESENTATIVE.

PACKAGING

Specifications	SOPRAPLY STICK DUO
Thickness	3.0 mm (118 mils)
Reinforcement	Composite
Dimensions	10 x 1 m (33 x 3.3 ft)
Weight	3.3 kg/m ² (0.7 lb/ft ²)
Selvedge width	100 mm (4 in)
Surface	Sanded
Underface	Self-adhesive, covered with a silicone release film

(All values are nominal)



SOPREMA.US • 1.800.356.3521

SOPREMA.CA • 1.877.MAMMOUTH

TDS_SOPRAPLY_STICK_DUO.indd

1/2

PROPERTIES

Properties	Standards	SOPRAPLY STICK DUO		
		BEFORE Heat Conditioning	AFTER Heat Conditioning	
Strain energy, min MD/XD At 23 °C ± 2 °C (73.4 °F ± 3.6 °F) At -18 °C ± 2 °C (0 °F ± 3.6 °F)	CSA A123.23-15, Type C, Grade 3	8/6.5 kN/m (46/37 lbf/in) 8/7 kN/m (46/40 lbf/in)	7/6 kN/m (40/34 lbf/in) 6.5/6 kN/m (37/34 lbf/in)	
Peak load, min MD/XD At 23 °C ± 2 °C (73.4 °F ± 3.6 °F) At -18 °C ± 2 °C (0 °F ± 3.6 °F)		17/14 kN/m (97/80 lbf/in) 22/19 kN/m (126/108 lbf/in)	18/15 kN/m (103/86 lbf/in) 22/17 kN/m (126/97 lbf/in)	
Elongation at peak load, min MD/XD At 23 °C ± 2 °C (73.4 °F ± 3.6 °F) At -18 °C ± 2 °C (0 °F ± 3.6 °F)		55/55 % 45/45 %	50/50% 35/35 %	
Ultimate elongation, MD/XD At 23 °C ± 2 °C (73.4 °F ± 3.6 °F)		65/65 %	55/55 %	
Dimensional stability, max MD/XD		±0.2/±0.2 %		
Low temperature flexibility, max MD/XD		-27/-27 °C (-17/-17 °F)	-18/-18 °C (0/0 °F)	
Compound stability at 91 °C (196 °F)		121/121 °C (250/250 °F)		
Resistance to puncture		Pass		
Water vapour transmission		ASTM E96 (Procedure B)	< 2.5 ng/Pa·s·m² (< 0.04 perm)	

(All values are nominal)

STORAGE AND HANDLING

Rolls must be stored upright, with the selvedge side on top. If the products are stored outdoors, cover them with an opaque protection cover after removal of the delivery packaging.



SOPREMA.US • 1.800.356.3521

SOPREMA.CA • 1.877.MAMMOUTH

TDS_SOPRAPLY_STICK_DUO.indd

2/2

This advice is given in good faith, for further advice or information do not hesitate to contact the allnex technical team.

Date: May 21

Replaces Sept 2015

Allnex Construction Products, a Division of Allnex New Zealand Ltd

Auckland - 14 Industry Road Penrose phone: 09-583-6544.

Hamilton - 18 Somerset Street Frankton phone: 07-847-8658

Wellington - Unit 9A: 4 Glover Street Ngauranga Gorge phone: 04-240-0305.

Christchurch - 112 Carlyle Street Sydenham phone: 03-366-6802

Customer Service: 0508-882-288 cs.constructionnz@allnex.com

www.allnexconstruction.com

DISCLAIMER: This information appearing in this Document (**Details**) concerning the product which is the subject of the Document (**Product**) is either based on present technical knowledge and tests done by allnex or tests done by, and data supplied from third parties including you, the customer. Since the actual use by you and by others of the Product is beyond the control of allnex, no warranty or representation, express or implied is made by allnex regarding the suitability for such use, nor does allnex accept any liability arising out of the use by you of other products or materials, whether third party or not, that may be referred to in this Document. allnex recommends that you carry out your own tests as to the suitability of the Product for your purpose, regarding which you accept full responsibility. In addition, if any of the Details appearing in the Document are based upon tests done by, and/or data supplied by any third party, allnex provides no warranties or representations in connection with those Details and you, the customer waives any right you may have against allnex in connection with the accuracy, completeness or otherwise of the Details. The information in this Document is not to be construed as absolutely complete or accurate since additional information may be necessary or desirable when particular or exceptional conditions or circumstances exist or because of applicable laws or government regulations affecting use of the Product. allnex does not provide any warranty or representation to you that the Product does not infringe the intellectual property rights of any third party. All orders accepted shall be subject to the standard conditions of sale of allnex which are on the back of our invoice. In accepting the Product you, the customer acknowledge and agree: **a.)** The Product is or may be of a hazardous nature and that you, the customer, are responsible for the disposal of the container housing the Product in accordance with the requirements and regulations of the relevant supervising government. **b.)** The Product has a limited shelf life and must be stored strictly in accordance with the guidelines and specifications related to it. **c.)** Where the Details relate to Product tested by allnex, those Details are indicative only, regarding which there may be batch to batch variation. **d.)** allnex gives no warranty or representation as to the applicability for the particular use by you, the customer, of the Product and you the customer shall be responsible for ensuring that the Product is fit for your intended use. **e.)** allnex's liability for breach of any term, condition, guarantee or warranty (express or implied and concerning the information in this Document or the Product more generally) including any liability for direct or indirect consequential loss (including indirect loss of profits), is limited to the maximum extent permitted by law and, at allnex's election, to either replacing or repairing the goods or paying the cost of replacing or repairing the goods, or in the case of services, supplying the services again.