

Technical Data Sheet



K102 Heavy Duty Epoxy Mortar System

DESCRIPTION:

K102 epoxy is an economical highly filled heavy duty epoxy mortar suitable for a wide variety of purposes.

TYPICAL FEATURES | BENEFITS:

- Simple 1:1 mix ratio.
- Two colours differentiate resin and hardener.
- User friendly.
- Very hard when cured
- Highly durable; high compressive strength
- Chemically resistant mortar
- Cure above +12°C.
- General purpose
- Hand mouldable
- Many uses, handy, paintable
- Easy mix recognition

PERFORMANCE DATA:

Properties		Values
Minimum application temperature: Air		+12°C
Flash point:	~ Resin ~ Hardener	>150°C >150°C
Tensile strength:		35 - 47.6 MPa
Tensile shear strength:		9 - 10 MPa
Compressive strength:		75 MPa
Flexural strength:		17 - 18 MPa
Modulus of elasticity:		2 x 10 ³ to 2.2 x 10 ³ MPa
Coefficient of linear expansion:		(25-60) (mm/mm/°) x10-6
Water absorption: ASTM D570: 10 days @25°C:		0.5 - 0.8% by weight
Maximum operating temperature:		+65°C
Potable Water Contact: -Suitable - Refer: Note 1 - Below Contact delay time with potable water after application.		Above +12°C minimum 24 hrs Below +12°C minimum 48 hrs
Adhesion Properties to correctly prepared surface:	~ Concrete ~ Metal ~ Timbers ~ PVC ~ Polyethylene ~ Polypropylene	Excellent Excellent Excellent Excellent Poor Refer: Note #2. -Below Poor Refer: Note #2. -Below
Appearance:	~ Resin ~ Hardener	Very thixotropic white mixture Very thixotropic black mixture
SG kg/litre:	~ Resin ~ Hardener	1.85 1.85
Density Kg/Litre -cured:		1.85
Coverage:		Use as required: (0.001m ³ = 1 Litre) e.g. 1 litre covers 1m ² @ 1mm thick
Pot Life: (Usable Life) Pot life is based on 100gram samples. Large quantities of mixed epoxy will generate heat and the pot life may be significantly reduced.	+12°C– 50%RH +15°C– 50%RH +20°C– 50%RH	40 - 50 minutes 20 - 30 minutes 15 - 20 minutes
Cure Time - Concrete Failure:		+18°C –50%RH 24 hours
Clean up:		Wash hands with warm soapy water after any skin contact Solvent HA for tools
NZ Dangerous Goods Class:		~ K102 Refer: SDS
Packaging:	~ K102 Kit ~ K102 Resin ~ K102 Hardener	2 litre 8 Litre 10 litre 10 litre
Shelf Life:		24 months from date of manufacture. (After this period consult with allnex).

Note #1.

Potable water: if the tank being mortared is for potable water use/storage. Take care to ensure the mix ratio is 1:1 and that the mortar is very uniformly mixed. Allow to cure and then wash and rinse out the tank prior to filling.

Suitable for potable water when mixed and cured correctly.

Note #2.

For bonding around Polyethylene & Polypropylene pipes in tanks/troughs etc. use allnex LM3000 followed by the use of K102.

RECOMMENDED USES:

- Grouting bolts into concrete: Horizontal & Vertical.
- Bonding pipes, concrete and PVC. Bends in concrete pipes.
- Re-forming edges; stair nosing's, usable overhead.
- Patching floor holes.
- Fixing pipes | concrete.
- Fixing floors, tanks, concrete blocks, kerbs.
- Filling holes, forming plinths.
- Chemically resistant mortar.

NOT RECOMMENDED:

- Application below +12°C air temperature.
- Bonding Polypropylene and polyethylene.
- Application to incorrectly prepared surfaces.
- Application to unsound substrates

HEALTH & SAFETY: Refer safety data sheets (SDS).

- Wear gloves wherever possible.
- Wash hands with warm, soapy water after any skin contact.
- Re-seal all containers tightly.

SURFACE PREPARATION:

The surface to be filled/repared must be clean and sound.

Remove all dust, dirt, oil, scale, laitance, paint or any other contaminates.

Concrete: Acid etch | Shot blast | Diamond grind | Needle gun.

Metals: Degrease with Acetone > Abrade with medium grit abrasive paper > Degrease with Acetone again.

Timber: Prepare by way of mechanical sanding using 80 grit paper

Spalled Concrete Control Joints: Diamond cut the spalled edges so that the face is vertical. Vacuum clean. > Fill > Recut

Note

K80 is best for Spalled Concrete Control Joints

MIXING RATIO

K102 Mixing Ratio - By weight

Element	Value
Resin	1 part
Hardener	1 part

K102 Mixing Ratio - By volume

Element	Value
Resin	1 part
Hardener	1 part

Refer: Cautions Section

The mix ratio must not be altered.

The mix ratio is the only acceptable formula.

Adding more hardener will make the mix softer and it will be uncured.

Increased hardener levels will result in a weaker product.

MIXING METHOD:

Carefully mix the product according to the stated mix ratio. Mix until uniform and no streakiness is evident. (Uniform grey colour)

May be hand mixed and moulded.

Mixing is often easiest with spade on the floor.

APPLICATION METHOD:

Hand moulded | Trowel | Spade.

Apply into place and smooth. – Non sag.

May be wetted with water to get a smooth glass like surface. - Excessive use of water will weaken the product.

Note

The installation of this product is speciality work and consideration should be given to the use of a competent installer.

CAUTION:

K102 is a two part epoxy that is mixed in a one-to-one ratio. Only this ratio will produce a hard, non-softening product. Adding more hardener (with the aim of making the product cure faster) will not work and will only result in making the product softer. The more hardener that is added, then the softer it will become. No matter how long it is left, it will never harden.

Only the stated mix ratio will work and exhibit the stated performance data.

Note well

The consequences of having soft K102 due to poor mixing may be far reaching and costly to repair. This is a job that must be done once, and done right. Many people do not understand the consequences.

One to one ratio mixing means just exactly that.

CAUTION:

K102 is a two part epoxy that is mixed in the specified ratio. Only this ratio will produce a hard, non-softening product. Adding more hardener (with the aim of making the product cure faster) will not work and will only result in making the product softer. The more hardener that is added, then the softer it will become. No matter how long it is left, it will never harden.

Only the stated mix ratio will work and exhibit the stated performance data.

Note

K102 is very tough and hard but it is not flexible. It will fill non-moving joints but will not bridge actively moving joints.

OTHER EPOXIES AVAILABLE:

- K36 - Clear Laminating Resin.
- K78 - Crack Repair.
- K80 - Pourable Grout.
- K83 – Machinable Epoxy Grout
- K102 - High Viscosity Mortar.
- K106 - Structural 24 hour Adhesive.
- K125 - Concrete Repair Paste.
- K130 - Control Joint Filler.
- K138- High Strength, Structural Heat Resistant Adhesive.
- K214 - General Purpose Adhesive
- K219- Structural 5 Minute Adhesive.
- K273- Underwater Cure Mortar.
- K2005 - High Peel Strength Structural Adhesive.
- Fairing Cream - Sandable Smoothing Paste.
- Truestik EA - Flexible Adhesive – Multipurpose.

EPOXY SELECTION:

Refer: Epoxy Selection Chart.

Date: August 2021
Replaces: Sept 2019

Allnex Construction Products, a Division of Allnex New Zealand Ltd
 Auckland - 14 Industry Road, Penrose. phone: 09-583-6544.
 Hamilton - 18 Somerset Street, Frankton. phone: 07-847-8658.
 Wellington - Unit 9A, 4 Glover Street, Ngauranga Gorge. phone: 04-240-0305.
 Christchurch - 112 Carlyle Street, Sydenham. phone: 03-366-6802.
 Customer Service: 0508-882-288 cs.constructionnz@allnex.com
www.allnexconstruction.com



DISCLAIMER: This information appearing in this Document (**Details**) concerning the product which is the subject of the Document (**Product**) is either based on present technical knowledge and tests done by allnex or tests done by, and data supplied from third parties including you, the customer. Since the actual use by you and by others of the Product is beyond the control of allnex, no warranty or representation, express or implied is made by allnex regarding the suitability for such use, nor does allnex accept any liability arising out of the use by you of other products or materials, whether third party or not, that may be referred to in this Document. allnex recommends that you carry out your own tests as to the suitability of the Product for your purpose, regarding which you accept full responsibility. In addition, if any of the Details appearing in the Document are based upon tests done by, and/or data supplied by any third party, allnex provides no warranties or representations in connection with those Details and you, the customer waives any right you may have against allnex in connection with the accuracy, completeness or otherwise of the Details. The information in this Document is not to be construed as absolutely complete or accurate since additional information may be necessary or desirable when particular or exceptional conditions or circumstances exist or because of applicable laws or government regulations affecting use of the Product. allnex does not provide any warranty or representation to you that the Product does not infringe the intellectual property rights of any third party. All orders accepted shall be subject to the standard conditions of sale of allnex which are on the back of our invoice. In accepting the Product you, the customer acknowledge and agree: **a.)** The Product is or may be of a hazardous nature and that you, the customer, are responsible for the disposal of the container housing the Product in accordance with the requirements and regulations of the relevant supervising government. **b.)** The Product has a limited shelf life and must be stored strictly in accordance with the guidelines and specifications related to it. **c.)** Where the Details relate to Product tested by allnex, those Details are indicative only, regarding which there may be batch to batch variation. **d.)** allnex gives no warranty or representation as to the applicability for the particular use by you, the customer, of the Product and you the customer shall be responsible for ensuring that the Product is fit for your intended use. **e.)** allnex's liability for breach of any term, condition, guarantee or warranty (express or implied and concerning the information in this Document or the Product more generally) including any liability for direct or indirect consequential loss (including indirect loss of profits), is limited to the maximum extent permitted by law and, at allnex's election, to either replacing or repairing the goods or paying the cost of replacing or repairing the goods, or in the case of services, supplying the services again.