

# Technical Data Sheet

## K130 Jointing and Filling Epoxy Urethane System



### DESCRIPTION:

K130 is a slightly flexible two part epoxy urethane compound for the filling of concrete control and construction joints.

### TYPICAL FEATURES | BENEFITS:

- Solvent free | No VOC's
- Tough, yet flexible
- User friendly.
- Supports concrete edges, prevents fretting and concrete edge chipping.
- Pourable and self-smoothing in joints but not too fluid that it runs excessively.
- Controls most standard control joint movements yet is tough and wear resistant.
- Two colours differentiate resin and hardener.
- Easy mix recognition.
- Ease of use in confined public areas.

### PERFORMANCE DATA:

Properties	Values
Minimum application temperature: Air	+12°C
Flash point: ~ Resin ~ Hardener	>150°C >94°C - Estimated
Maximum recommended movement capability:	5%
Compressive strength:	40 MPa
Shore A Hardness:	80
Maximum operating temperature:	+75°C
Adhesion Properties to correctly prepared surface: <i>Note</i> <i>Primarily designed for concrete joints</i> <i>But will bond to metal and timber</i> ~ Concrete ~ Metal ~ Timbers	Excellent Excellent Excellent
Appearance: ~ Resin ~ Hardener	Filled Liquid - Colours Viscous Amber Liquid
SG kg/litre: ~ Resin ~ Hardener	1.1 1.0
Density Kg/Litre -cured:	1.05
Coverage:	Use as required: (0.001m <sup>3</sup> = 1 Litre) e.g. 1 litre covers 1m <sup>2</sup> @ 1mm thick
Pot Life: (Usable Life) Pot life is based on 100gram samples. Large quantities of mixed epoxy will generate heat and the pot life may be significantly reduced.	+12°C– 50%RH 40 minutes +15°C– 50%RH 30 minutes +20°C– 50%RH 15 - 20 minutes
Cure Time:	+20°C –50%RH 12 - 24 hours
Clean up:	Wash hands with warm soapy water after any skin contact Solvent HA for tools
NZ Dangerous Goods Class: ~ K130	Refer: SDS
Packaging: ~ K130 Kit	2 Litre
Shelf Life:	12 months from date of manufacture. (After this period consult with allnex).

### RECOMMENDED USES:

- Concrete control Joints.
- Joints between dissimilar materials.
- Joints in synthetic polymer toppings e.g.: Terrazzite | Sureshield.
- Concrete construction joints.
- Adhesive for dissimilar materials.
- Speciality adhesive.

**NOT RECOMMENDED:**

- Application below +12°C air temperature.
- Application to incorrectly prepared surfaces.
- Application to unsound substrates.
- Bonding Polypropylene and polyethylene.

**HEALTH & SAFETY:** Refer safety data sheets (SDS).

- Wear gloves wherever possible.
- Wash hands with warm, soapy water after any skin contact.
- Re-seal all containers tightly.

**SURFACE PREPARATION:**

The surface to be filled/repared must be clean and sound.

Remove all dust, dirt, oil, scale, laitance, paint or any other contaminates.

Concrete: Acid etch | Shot blast | Diamond grind | Needle gun.

Metals: Degrease with Acetone > Abrade with medium grit abrasive paper > Degrease with Acetone again.

Timber: Prepare by way of mechanical sanding using 80 grit paper.

Concrete Control Joints: Diamond cut the spalled edges so that the face is vertical. Vacuum clean.

**JOINT DESIGN:**

Joints are typically a minimum of 6-12mm across.

Depth of joint must not exceed width of joint.

Delay joint installation until the maximum amount possible of concrete shrinkage has occurred.

Joint width must be designed to accommodate anticipated movement taking into account the movement capability of K130.

K130 is to be adhered to the two joint sides only.

**Note**

Three point adhesion. I.e. to the base, will limit K130 elongation. This will likely lead to cracking or splitting.

**MIXING RATIO****K130 Mixing Ratio - By weight**

Element	Value
Resin	3.4 part
Hardener	1 part

**K130 Mixing Ratio - By volume**

Element	Value
Resin	3 part
Hardener	1 part

*Refer: Cautions Section*

The mix ratio must not be altered.

The mix ratio is the only acceptable formula.

Adding more hardener will make the mix softer and it will be uncured.

Increased hardener levels will result in a weaker product.

**MIXING METHOD:**

Carefully mix the product according to the stated mix ratio. Mix until uniform and no streakiness is evident. (Uniform grey colour)

Hand mixed.

Mixing is often easiest with gauging trowel or broad knife.

**COLOUR MIXING:**

Other colours may be created by tinting K130 off-white

Tint	Addition Rate	Method
Light grey	Add: 2 grams or 2mls black B1TTP tinter per 2lt K130 off white kit	add to resin and premix before hardener is added
Dark grey	Add: 15 grams or 15mls black B1TTP tinter per 2lt K130 off white kit	add to resin and premix before hardener is added

**MIXING METHOD:**

After any tinting; Carefully mix the product according to the stated mix ratio, carefully and slowly.

Mix until uniform and no streakiness is evident.

Aeration of the mix can result in blistering of the K130 joint surface.

With K130, mixing is critical. Unmixed K130 will result in soft patches in the joint.

May be slow drill mixed. (200-300rpm).

Avoid air entrainment when mixing.

Normally mix full kits to avoid mixing errors.

## APPLICATION METHOD:

Trowel | Knife | Cartridge | Barrel gun | Pourable

Ensure the joint sides are freshly cut, clean and dry.

Ensure the joint base is clean. Use PEF foam rod or bond breaker tape as appropriate.

Tape the surface of the sides of the joint and bag in the mixed K130.

Tool off the excess carefully and remove the tape.

Protect the area until cured.

### Note

For polished floors, a K130 joint can be overfilled and may be ground flat during the grinding/polishing process.

### Note

The installation of this product is speciality work and consideration should be given to the use of a competent installer.

## CAUTION:

K130 is a two part epoxy that is mixed in the specified ratio. Only this ratio will produce a hard, non-softening product. Adding more hardener (with the aim of making the product cure faster) will not work and will only result in making the product softer. The more hardener that is added, then the softer it will become. No matter how long it is left, it will never harden.

**Only the stated mix ratio will work and exhibit the stated performance data.**

## Note well

The consequences of having soft K130 due to poor mixing may be far reaching and costly to repair.

This is a job that must be done once, and done right. Many people do not understand the consequences.

## OTHER EPOXIES AVAILABLE:

- K36 - Clear Laminating Resin.
- K78 - Crack Repair.
- K80 - Pourable Grout.
- K83 – Machinable Epoxy Grout
- K102 - High Viscosity Mortar.
- K106 - Structural 24 hour Adhesive.
- K125 - Concrete Repair Paste.
- K130 - Control Joint Filler.
- K138- High Strength, Structural Heat Resistant Adhesive.
- K214 - General Purpose Adhesive
- K219- Structural 5 Minute Adhesive.
- K273- Underwater Cure Mortar.
- K2005 - High Peel Strength Structural Adhesive.
- Fairing Cream - Sandable Smoothing Paste.
- Truestik EA - Flexible Adhesive – Multipurpose.

## EPOXY SELECTION:

Refer: Epoxy Selection Chart.

Date: August 2021

Replaces: Sept 2019

### Allnex Construction Products, a Division of Allnex New Zealand Ltd

Auckland - 14 Industry Road, Penrose. phone: 09-583-6544.

Hamilton - 18 Somerset Street, Frankton. phone: 07-847-8658.

Wellington - Unit 9A, 4 Glover Street, Ngauranga Gorge. phone: 04-240-0305.

Christchurch - 112 Carlyle Street, Sydenham. phone: 03-366-6802.

Customer Service: 0508-882-288 [cs.constructionnz@allnex.com](mailto:cs.constructionnz@allnex.com)

[www.allnexconstruction.com](http://www.allnexconstruction.com)



**DISCLAIMER:** This information appearing in this Document (**Details**) concerning the product which is the subject of the Document (**Product**) is either based on present technical knowledge and tests done by allnex or tests done by, and data supplied from third parties including you, the customer. Since the actual use by you and by others of the Product is beyond the control of allnex, no warranty or representation, express or implied is made by allnex regarding the suitability for such use, nor does allnex accept any liability arising out of the use by you of other products or materials, whether third party or not, that may be referred to in this Document. allnex recommends that you carry out your own tests as to the suitability of the Product for your purpose, regarding which you accept full responsibility. In addition, if any of the Details appearing in the Document are based upon tests done by, and/or data supplied by any third party, allnex provides no warranties or representations in connection with those Details and you, the customer waives any right you may have against allnex in connection with the accuracy, completeness or otherwise of the Details. The information in this Document is not to be construed as absolutely complete or accurate since additional information may be necessary or desirable when particular or exceptional conditions or circumstances exist or because of applicable laws or government regulations affecting use of the Product. allnex does not provide any warranty or representation to you that the Product does not infringe the intellectual property rights of any third party. All orders accepted shall be subject to the standard conditions of sale of allnex which are on the back of our invoice. In accepting the Product you, the customer acknowledge and agree: **a.)** The Product is or may be of a hazardous nature and that you, the customer, are responsible for the disposal of the container housing the Product in accordance with the requirements and regulations of the relevant supervising government. **b.)** The Product has a limited shelf life and must be stored strictly in accordance with the guidelines and specifications related to it. **c.)** Where the Details relate to Product tested by allnex, those Details are indicative only, regarding which there may be batch to batch variation. **d.)** allnex gives no warranty or representation as to the applicability for the particular use by you, the customer, of the Product and you the customer shall be responsible for ensuring that the Product is fit for your intended use. **e.)** allnex's liability for breach of any term, condition, guarantee or warranty (express or implied and concerning the information in this Document or the Product more generally) including any liability for direct or indirect consequential loss (including indirect loss of profits), is limited to the maximum extent permitted by law and, at allnex's election, to either replacing or repairing the goods or paying the cost of replacing or repairing the goods, or in the case of services, supplying the services again.